



Product Information:  
**ANKOR D**  
**Corrosion Preventative**

**Description:**

Ankor D is a special solvent deposited, short to medium term rust preventative. This product has a very low surface tension and viscosity and therefore spreads rapidly, penetrating into all hard to reach parts and covering all surfaces however irregular. It dries to leave a continuous protective coating of viscous petroleum products and additives that have powerful rust preventative properties. This product is particularly useful where the metal parts to be treated are wet, because the chemistry of Ankor D has powerful attraction to the metal surface and this completely displaces all traces of water before laying down the protective rust preventing film. Ankor D is very effective as a rust preventative in damp atmospheres and all climates.

**Applications:**

Ankor D is recommended for all short and medium term rust proofing. It is particularly suitable for use in machine shops as an inter operation rust preventative for wet parts. This product is also highly recommended for protecting bright steel wire, bars, billets, sections and sheets during storage and transport.

Ankor D can be applied by spraying, brushing or dipping. The low viscosity of this product ensures minimum drag out when using the dipping process, and in large scale systems this can show significant saving, over other types of products.

The product is ready for use straight from the drum, no stirring or mixing is required, however, the drum must be kept closed to avoid excessive evaporation of the solvent. If parts that have been treated with Ankor D are to be subsequently painted, the coating must be removed prior to painting and this can be achieved using our Tabor OK or Purolene. White spirit, kerosene and other hydrocarbon solvents may also be used.

**Protection Performance:**

- ✓ Indoors 12 months
- ✓ Covered Outdoors 6 months
- ✓ Outdoors 3 months

**Physical Characteristics:**

Appearance	Dark Amber liquid
Density @ 15°C	0.825
Viscosity @ 40°C (cSt)	3.5
Closed Flash Point (°C)	50
Film Thickness (µm)	6.4
Drying time @ 20 °C	90
Dewatering	Yes

Figures based on average production values

Part No.s: AND025, AND205

(TDS Ankor D – 161215 Issue 4)

